

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : G11B	A2	(11) International Publication Number: WO 98/31011 (43) International Publication Date: 16 July 1998 (16.07.98)
(21) International Application Number: PCT/US98/00348 (22) International Filing Date: 9 January 1998 (09.01.98) (30) Priority Data: 08/782,555 10 January 1997 (10.01.97) US (71) Applicant: WEA MANUFACTURING, INC. [US/US]; 1444 East Lackawanna Avenue, P.O. Box 321, Olyphant, PA 18447 (US). (71)(72) Applicants and Inventors: MARQUARDT, Richard, Jr. [US/US]; 229 Cornell Avenue, Clarks Green, PA 18411 (US). COOKSON, Christopher [US/US]; 7825 Torreyson Drive, Los Angeles, CA 90046 (US). PIETRZYKOSKI, Anthony [US/US]; 30 Birch Lane, Hudson Gardens, Plains, PA 18705 (US). OREHOTSKY, John, L. [US/US]; 79 Grandview Avenue, Dallas, PA 18612 (US). CAREY, Deborah, H. [US/US]; 38 Fifth Street, Wyoming, PA 18644-2126 (US). PRICE, Howard, L. [US/US]; 9637 Hammett Parkway, Norfolk, VA 23503-1709 (US). PINDZOLA, Daniel, M. [US/US]; 236 Country Road, Berqyn, PA 19312 (US). (74) Agent: RUBENSTEIN, Allen, I.; Gottlieb, Rackman & Reisman, P.C., 8th floor, 270 Madison Avenue, New York, NY 10016 (US).		(81) Designated States: AU, CN, JP, SG, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>Without international search report and to be republished upon receipt of that report.</i>
(54) Title: MULTI-SURFACED, SINGLE SIDED OPTICAL DISC		
<p style="text-align: center;">$\lambda = 650\text{nm}$ $\lambda = 780\text{nm}$</p>		
(57) Abstract A double sided (or higher multiple sided) data storing compact disc for optically recorded data has data surfaces that are separated by a thin film of wavelength selective material that passes light of one frequency and reflects light of a second (or multiple) frequency. The thin film either passively relies upon the inherent interference between light signals reflected from its upper and lower surfaces or is an active material that reflects light of one frequency and transmits light of a second frequency. A further aspect of the present invention is the method for the manufacture of such a multi-surfaced disc.		

BEST AVAILABLE COPY

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

MULTI-SURFACED, SINGLE SIDED OPTICAL DISC
FIELD OF THE INVENTION

5 This invention relates to optical storage media, specifically compact discs that contain more than one data recording surface readable from a single side of the disc.

BACKGROUND OF THE INVENTION

10 Compact discs are typically composite objects having a series of pits impressed into a plastic surface, usually during an injection molding process. These pits and the lands between them are arranged in a spiral pattern that can be tracked by a pickup laser beam which advances slowly along a radius of the disc while the disc is spun about an axis through the center of the disc. The pit/land surface is coated with a thin reflective metal layer. The pickup laser beam is reflected from the metal layer coating the pits and lands and the reflection is analyzed to observe the change in reflection intensity associated with a transition from a land to a pit or vice versa. To enhance the change in reflection intensity the wavelength of light is chosen to cause interference when the laser illuminates a pit. The interference occurs between laser light reflected from the bottom of a pit and light reflected from the areas outside the pits struck by the laser light. Therefore the wavelength of light is not chosen arbitrarily, but is typically related to the depth of the pits. An infrared wavelength of 780-790 nm in air (503-510 nm in polycarbonate where the index of refraction $n=1.55$) is often used. By detecting the change in reflection intensity, the length

15
20
25
30
35

of the pit and or land as it passes under the pickup laser is sensed by photocells and is then interpreted by the CD player's electronics. Data is encoded onto the compact disc as
5 varying lengths of the pits and lands. The data may be analog or digital data. For example a voltage level may correspond to a pit length in an analogue recording, or the length of the pits/lands may represent strings of 0's
10 or 1's for the recording of digital data.

The amount of data that can be encoded onto a disc is limited by the density of pits and lands that can be accurately reproduced, for example by an injection molding procedure, and that can be accurately read by a
15 photocell sensor system. Some error rate can be tolerated if the data is placed on the disc in a redundant format that allows errors to be recognized and corrected. Thus as the pits and
20 lands are decreased in size it becomes necessary as a practical matter to provide greater redundancy in the data until a limit is reached in the amount of data that can be stored on the disc surface.

25 The conventional audio compact disc stored data that was readable from only one side, the other side being used to display a label over the surface of the disc. It has been known to utilize both surfaces of the compact disc to
30 store data, thereby doubling the amount of data that can be stored. Double sided discs have been made by fabricated two half thickness compact discs and bonding them back to back. One drawback of such a product is that the disc
35 must be removed from the player and inverted if there is only one pickup laser reading head within the player, or multiple reading heads

must be provided. The present invention avoids the need for either multiple reading heads or disc inversion.

BRIEF DESCRIPTION OF THE INVENTION

5 A CD format using a reading beam of shorter than conventional wavelength (650 nm v. 780 nm) called DVD has been proposed. Discs for this new format would not be readable by conventional CD players. The present invention
10 provides a way to have an optical disc medium readable by both (conventional) CD and DVD players.

 The present invention provides a double surfaced (or higher multiple surfaced) data
15 storing compact disc for optically recorded data. The data surfaces (one for convention CD, one for DVD) are separated by a thin film of wavelength sensitive material that passes light of one frequency and reflects light of a
20 second (or multiple) frequency. The thin film may provide this effect by passively relying upon the inherent interference between light signals reflected from the upper and lower surfaces of the film. In another embodiment
25 the thin film may be fabricated from an active material that receives light of one frequency and depending upon that frequency remits light of a second frequency. Filtering optics can then distinguish the light reflected from the
30 data surfaces. In this manner, by the proper selection of the wavelength of the illuminating light the information stored in the pits and lands of the appropriate surface is selectively recovered from the compact disc.

35 A further aspect of the present invention is the method for the manufacture of such a

multi-surfaced disc. The invention is a combination of the technologies of compact disc manufacture and thin film technology.

5 One advantage of the present invention is greater information storage on a single disc. A second advantage is that by providing a disc with two different data formats it may allow backwards compatibility during introduction of a new DVD format.

10 **BRIEF DESCRIPTION OF THE DRAWINGS**

Figure 1 is a schematic representation of the reflection of light from a thin film.

Figure 2 is a side cut away view showing the data recording surfaces of the present invention.

15 Figure 3 is a further embodiment in which the wavelength selectable thin film comprises the adhesive bonding the CD and DVD surfaces together.

20 Figure 4 is a structural diagram of a preferred thin film material.

Figure 5 is a schematic view of an alternative embodiment of the present invention employing multiple data surfaces.

25 **DETAILED DESCRIPTION OF A PREFERRED EMBODIMENT**

Figure 1 shows the reflection of parallel rays of light from two surfaces of a thin film. The light is shown in non-normal incidence for purposes of clarity, but in practice the light is normally incident on the film. The phase change of the ray that takes the longer path by reflection from the upper surface is $2\pi(2d_i/\lambda_i) + [\pi]$, where the $[\pi]$ term is included if the light is reflected from a surface having a lesser index of refraction than the material

through which it is propagating. The index i identifies the layer where the reflection takes place in the event that there is more than one such layer. When the phase change is an odd multiple of π relative to the ray reflected from the lower surface, there is destructive interference and the intensity of the light reflected from the thin film as a whole is reduced and the wave propagates through the thin film. In this manner any thin film of proper thickness and index of refraction has wavelength selective properties. In one aspect of the present invention a thin film coating is used to select between the different wavelengths of the pickup lasers.

Figure 2 depicts a cross section (not to scale) through a portion of the compact disc of the present invention. The pits and lands are present on two levels. The upper level pits and lands 11 are formed on a PCV or polycarbonate vinyl flat surface termed the CD 13, because of its resemblance to conventional audio or CD-ROM surfaces. It is coated with a metalization layer 15 to enhance the reflectivity of light entering from below. The depths of the pits on the CD layer are such as to enhance interference effects when 780 nm radiation is incident on the pit/land surface. The lower level pits and lands 17 are formed on a PCV flat surface termed the DVD 19. The lower level pits and lands are coated with a wavelength selective reflection layer 21, also referred to as a thin film layer, thereby completing the formation of the DVD. Both the DVD and the CD layers have preferred thicknesses of 0.6 mm. The thin film layer 21 is preferably a silicon carbide (SiC $n=2.7$), oxide

or nitride deposited by sputtering onto the appropriate surface to a thickness of approximately 140 nm. The two layers are adhered together by an bonding layer 23, which may be a transmissive photo polymer layer having a thickness of 30-40 μ . In an alternative embodiment of the present invention depicted in Figure 3, the adhesive material may itself constitute the wavelength selective thin film. The thin film layer 21 is reflective to wavelengths of 650 nm and transmissive to infrared wavelengths of 780 nm. In the preferred embodiment the wavelength selection is a function of the thin film nature of the sputtered material and not any particular active feature of the silicon material.

In an alternative embodiment the DVD layer 19 comprises a dye polymer layer 21, which is over 85% transmissive to 780 nm light and over 15% reflective to 650 nm light. In both embodiments, the CD layer is conventionally coated (metallized) for maximum reflectivity of over 90%. The relative efficiency of the reflectivity of the 780 nm material is 70%. The data density of the DVD layer may be reduced to 4.5 gigabytes to assure adequate signal to noise ratio.

This application contains three alternative embodiments of the invention using active materials. These are the use of an organic dye, the use of a semiconductor having a large index of refraction for reflectivity, and the use of a liquid crystal polymer, and the use of an emission/transmission design.

In a first alternative embodiment, a thin (i.e., molecular) layer of an organic dye having the desired reflectivity at 650 nm and

transmissivity at 780 nm is place on the surface of the polycarbonate disc. The two polycarbonate discs are then bonded together with an aliphatic hydrocarbon wax, strengthened by a small amount of ethylene vinyl acetate (EVA). These polymers are transmissive to 780 nm. The system is easily adaptable to large-scale manufacturing. The dye may be selected from a group that are transmissive at 780 nm and reflective at 650 nm. This dyes include the anthraquinones, such as D&C green 6 (1,4-di(p-toluidine)anthraquinone) available from Crompton & Knowles, and solvent green 6, available from Pylam. Other useable dyes are Chlorantine Fast Blue 4GL and diphenylmethine dyes such as Michler's hydrol. The structural diagrams for these preferred dyes are shown in Figure 4.

To apply the D&C green 6 dye onto the surface of a polycarbonate disc the dye is dissolved in USP No. 10 mineral oil and then spin-cast onto the surface of the disc prior to adding the adhesive. The mineral oil is preferred because it is transparent at the wavelengths of interest and will flow evenly into the imprinted grooves of the disc due to its low viscosity.

Reflection occurs only at the interface between the dye and the polycarbonate disc, and therefore, only a uniform molecular layer is necessary for this embodiment to work. 5-10 μm of the dye is sufficient to cover the surface of the disc. An alternative technique to spin-casting a thin layer of the dye onto the disc is to use a solvent such as butane that could be flashed evaporated. In this process, rapid heating of the solvent would leave the dye be-

hind on the surface of the disc.

To bond the discs a strong adhesive for polycarbonate is used such as pure paraffin or micro-crystalline waxes. These have a melting
5 temperature around 80°C and readily "wet" the surface of polycarbonate. In addition to their adhesive strengths, any residual hydrocarbon solvent used for dissolving the dye would be absorbed by these waxes and would concentrate
10 the D&C green 6 into a very compact reflective layer at the surface of the disc. A small percentage of ethylene vinyl acetate (EVA) (10%) should be added to the paraffin wax melt, to increase the high temperature tensile
15 strength and low temperature flexibility of the product. Adding more than 10% of EVA to the paraffin wax may cause cloud point dispersion of the light beam, which might diminish the signal intensity.

In a second preferred embodiment of the present invention a semiconductor may be used to bring about the desired wavelength selectivity. The preferred semiconductor is a
20 (GaAs)_{0.6}(GaP)_{0.4} stoichiometric III-V semiconductor. At 500 nm, the index of refraction of this material is about 3.5, so the reflectivity is measurable at 650 nm. The index of refraction of the polycarbonate is 1.5. The reflectivity at an interface is calculate from $R = (n_2 - n_1 / n_2 + n_1)^2$. Thus at a (GaAs)_{0.6}(GaP)_{0.4} / air
25 interface the reflectivity is $(3.5 - 1)^2 / (3.5 + 1)^2 = 30\%$. At a (GaAs)_{0.6}(GaP)_{0.4} / polycarbonate interface the reflectivity is $R = (3.5 - 1.5)^2 / (3.5 + 1.5)^2 = 16\%$. Because of the reflection at the polycarbonate air interface a total
30 reflectivity of about 10% is expected in the CD/DVD technology with this material as the

filter. This 10% reflectivity represents an attenuated signal, but is expected to be serviceable for the technology provided the incident laser power is sufficiently intense, the
5 optical detection system is sufficiently sensitive and the remaining 90% of the incident 650 nm radiation is accommodated by absorption effects and not transmissivity.

The CD/DVD technology requires a material
10 with a very sharp change in the transmissivity at about 700 nm. This requires a change of the absorption coefficient by orders of magnitude in the immediate vicinity of 700 nm. This is satisfied by semiconducting materials with band
15 gap energies of approximately 1.7 eV. The preferred material, $(\text{GaAs})_{.6}(\text{GaP})_{.4}$ stoichiometric II-V semiconductor, has this desired band gap energy. The sharpness of the transmissivity has been evaluated from the wavelength dependence of the absorption coefficient, which shows that the absorption coefficient can change by about 5 orders of magnitude
20 over a 100 nm wavelength band centered about 700 nm. At 650 nm the internal transmissivity is negligibly small. At 780 nm the internal transmissivity is 100%. The reflectivity at
25 780 nm is in excess of 10%, since the refractive index generally decreases with increasing wavelength.

30 To achieve larger reflectivity than 10% at 650 nm, a very thin (about 10 nm) partially reflective chromium layer can be deposited on the polycarbonate prior to depositing the 40 μm GaAsP layer. Increasing the reflectivity to
35 specifications at 650 nm with a partially transmissive chromium layer will have an attenuating effect on the transmissive behavior at

780 nm. A beneficial side-effect of employing chromium as a reflectivity agent is that it may also be strong bonding agent between the polycarbonate and the GaAsP.

5 Other materials having a band gap energy at 1.7 eV is the II-VI binary compound CdSe. However its index of refraction is about 2.5, making it less suitable. Several ternary and quaternary III-V compound semiconductors exist
10 whose binary compound components are mutually soluble in each other and whose compositions can be adjusted to achieve a 1.7 eV band gap energy. The ternary $(\text{GaAs})_{1-x}(\text{AlAs})_x$ compounds represent alternative possibilities to the
15 preferred GaAsP system.

 A still further preferred embodiment employs a liquid crystal polymer (LCP). LCPs are polymers whose optical properties are controlled by the molecular structure and the
20 post-reactor processing involving thermal, mechanical and electrical energy. The optical properties are also changed by processing the polymer by itself or with other polymers.

 In the prior art, LCP's have been used for
25 a wide variety of optical devices. These include switchable optical recording medium, gas flow optical indicator, light modulators, shutters and valves, amplitude intensifying optical filters, wave plate for 1054 nm laser,
30 optical bandpass filter, multipage optical display as well as other applications. LCPs have been applied as films and as dispersions in other polymers including polycarbonate. The composite is a polymer dispersed liquid crystal
35 or PDLC. The PDLC contains "droplets" of the LCP. The size, pitch and spatial orientation of these droplets provide yet another way of

controlling the optical properties of the polymer-LCP composite.

5 A copolyamide of nylon 6 and nylon 66 with the trade name Utramid is supplied by BASF. This contains no chopped glass reinforcing fibers, so it is useful for optical applications.

10 The general method of dispensing LCPs in host polymers is by extrusion. Such dispersion can be done prior to and independent of the present manufacturing line.

15 A still further preferred embodiment is shown in Figure 5. There, a multilayered example of the present invention is depicted in which there are more than two data recording surfaces.

20 A particular utility for this invention is to provide a single compact disc that is readable both on a conventional CD player (where the data is read using the longer wavelength light that passes through the DVD layer) and on a DVD format player. The DVD player requires a thinner plastic layer that allows the DVD data surface to be closer to the pickup laser. This is accomplished by the present invention where, as shown in Fig. 2, the DVD layer is closer to the pickup optics. The CD player, which can tolerate a greater displacement between the pickup optics and the data surface is the surface further removed from the pickup optics.

25 In this manner, a disc may be prepared which could be used with either a CD or DVD player by having data for the corresponding player on the corresponding layer.

30

35 While there have been shown and described and pointed out the fundamental novel features of the invention as applied to preferred

embodiments thereof, it will be understood that various omissions and substitutions and changes in the form and details of the device illustrated and in its operation may be made by those skilled in the art without departing from the spirit of the invention.

What is claimed is:

1. A multi layer data storage medium for data optically recorded in pit and land structures having data a portion of which is readable by light of a first frequency and not by light of a second frequency and a portion of which data is readable by light of a second frequency and not the first frequency, comprising

10 a first data surface formed as a series of pits and lands in a first plastic layer,

15 a thin film of material forming a layer having upper and lower surfaces said lower surface in contact with the pits and lands of said first data surface, wherein said film passes light of the second frequency and reflects light of the first frequency,

20 an adhesive layer in contact with the upper surface of said thin film, said adhesive layer being transparent to light of the second frequency,

25 a second plastic layer in contact with said adhesive, said second plastic layer having a second data surface comprising a series of pits and lands remote from said adhesive,

30 a reflective layer for said second frequency of light in contact with the second data surface.

2. The multilayer data storage medium of claim 1, wherein said thin film is reflective to wavelengths of 650 nm and transmissive to infrared wavelengths of 780 nm.

35 3. The multilayer data storage medium of

claim 1, wherein said surfaces of said thin film are separated by a thickness to cause destructive interference between light of the second frequency reflected from its upper and lower surfaces.

4. The multilayer data storage medium of claim 3, wherein said thin film is reflective to wavelengths of 650 nm and transmissive in infrared wavelengths of 780 nm.

10 5. The multilayer data storage medium of claim 3, wherein said reflective layer is a metallization layer.

15 6. The multilayer data storage medium of claim 5, wherein said reflective layer has a reflectivity of over 90%.

7. The multilayer data storage medium of claim 3, wherein said plastic layers have a thickness of 0.6 mm.

20 8. The multilayer data storage medium of claim 3, wherein said adhesive layer is a transmissive photo polymer.

9. The multilayer data storage medium of claim 8, wherein said adhesive layer has a thickness of approximately 30-40 μ .

25 10. The multilayer data storage medium of claim 3, wherein said thin film is selected from the group consisting of silicon carbide, silicon oxide or silicon nitride.

11. The multilayer data storage medium of

claim 10, wherein said thin film has a thickness of approximately 140 nm.

5 12. The multilayer data storage medium of claim 1, wherein said thin film comprises a dye polymer.

13. The multilayer data storage medium of claim 12, wherein said dye polymer is over 85% transmissive to 780 nm light and over 15% reflective to 650 nm light.

10 14. The multilayer data storage medium of claim 12, wherein said reflective layer has a reflectivity of over 90%.

15 15. The multilayer data storage medium of claim 1, wherein said thin film comprises a material selected from the group consisting of an organic dye, a semiconductor having a large index of refraction for reflectivity, and a liquid crystal polymer.

20 16. The multilayer data storage medium of claim 15, wherein said thin film comprises an organic dye transmissive at 780 nm and reflective at 650 nm.

25 17. The multilayer data storage medium of claim 16, wherein said organic dye is selected from the group consisting of anthraquinones, and diphenylmethine dyes.

30 18. The multilayer data storage medium of claim 15, wherein said adhesive is a mixture of aliphatic hydrocarbon wax and ethylene vinyl acetate.

19. The multilayer data storage medium of claim 18, wherein said adhesive is paraffin or a micro-crystalline wax.

5 20. The multilayer data storage medium of claim 15, wherein said thin film comprises a semiconducting material with a band gap energy of approximately 1.7 eV.

10 21. The multilayer data storage medium of claim 20, wherein said semiconducting material is a Ga stoichiometric semiconductor.

22. The multilayer data storage medium of claim 21 further comprising a partially reflective chromium layer between the plastic layer and the Ga semiconductor.

15 23. The multilayer data storage medium of claim 20, wherein said thin film comprises CdSe.

20 24. The multilayer data storage medium of claim 15, wherein said liquid crystal polymer comprises a polymer dispersed liquid crystal.

25 25. The multilayer data storage medium of claim 24, wherein said liquid crystal polymer is a copolyamide of nylon 6 and nylon 66.

26. A multilayer data storage medium for data optically recorded in pit and land structures having data a portion of which is readable by light of a first frequency and not by light of a second frequency and a portion of which data is readable by light of a second frequency and not the first frequency,
30

comprising

a first data surface formed as a series of pits and lands in a first plastic layer,

5 a layer of adhesive material having upper and lower surfaces said lower surface in contact with the pits and lands of said first data surface, wherein said layer of adhesive passes light of the second frequency and
10 reflects light of the first frequency, said adhesive layer being transparent to light of the second frequency,

a second plastic layer in contact with said adhesive layer, said second plastic
15 layer having a second data surface comprising a series of pits and lands remote from said adhesive layer,

a reflective layer for said second frequency of light in contact with the second
20 data surface.

27. The multilayer data storage medium of claim 26, wherein said surfaces of said adhesive layer are separated by a thickness to cause destructive interference between light of
25 the second frequency reflected from its upper and lower surfaces.

28. The multilayer data storage medium of claim 27, wherein said thin film is reflective to wavelengths of 650 nm and transmissive to
30 infrared wavelengths of 780 nm.

29. The multilayer data storage medium of claim 27, wherein said reflective layer is a metallization layer.




30. The multilayer data storage medium of claim 27, wherein said plastic layers have a thickness of 0.6 mm.

5 31. The multilayer data storage medium of claim 27, wherein said adhesive layer is a transmissive photo polymer.

32. The multilayer data storage medium of claim 31, wherein said adhesive layer has a thickness of approximately 30-40 μ .

10 33. The multilayer data storage medium of claim 27, wherein said thin film is selected from the group consisting of silicon carbide, silicon oxide or silicon nitride.

15 34. The multilayer data storage medium of claim 33, wherein said thin film has a thickness of approximately 140 nm.



2 / 3

ORGANIC DYES THAT ARE TRANSMISSIVE AT 780nm AND REFLECTIVE AT 650 nm




FIG. 4

3 / 3





FIG. 5

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : G11B 7/24, 3/70, 3/74		A3	(11) International Publication Number: WO 98/31011
			(43) International Publication Date: 16 July 1998 (16.07.98)
(21) International Application Number: PCT/US98/00348		(81) Designated States: AU, CN, JP, SG, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).	
(22) International Filing Date: 9 January 1998 (09.01.98)			
(30) Priority Data: 08/782,555 10 January 1997 (10.01.97) US		Published With international search report.	
(71) Applicant: WEA MANUFACTURING, INC. [US/US]; 1444 East Lackawanna Avenue, P.O. Box 321, Olyphant, PA 18447 (US).		(88) Date of publication of the international search report: 12 November 1998 (12.11.98)	
(71)(72) Applicants and Inventors: MARQUARDT, Richard, Jr. [US/US]; 229 Cornell Avenue, Clarks Green, PA 18411 (US). COOKSON, Christopher [US/US]; 7825 Torreyson Drive, Los Angeles, CA 90046 (US). PIETRZYKOSKI, Anthony [US/US]; 30 Birch Lane, Hudson Gardens, Plains, PA 18705 (US). OREHOTSKY, John, L. [US/US]; 79 Grandview Avenue, Dallas, PA 18612 (US). CAREY, Deborah, H. [US/US]; 38 Fifth Street, Wyoming, PA 18644-2126 (US). PRICE, Howard, L. [US/US]; 9637 Hammett Parkway, Norfolk, VA 23503-1709 (US). PINDZOLA, Daniel, M. [US/US]; 236 Country Road, Berwyn, PA 19312 (US).			
(74) Agent: RUBENSTEIN, Allen, I.; Gottlieb, Rackman & Reisman, P.C., 8th floor, 270 Madison Avenue, New York, NY 10016 (US).			

(54) Title: MULTI-SURFACED, SINGLE SIDED OPTICAL DISC



(57) Abstract

A double sided data storing compact disc (13, 19) for optically recorded data has data surfaces (15, 21) bonding (23) together and separated by a thin film of wavelength selective material that passes light of one frequency (780 nm) and reflects light of a second frequency (650 nm), the thin film either passively relies upon the inherent interference between light signals reflected from its upper and lower surfaces or is an active material that reflects light of one frequency and transmits light of a second frequency.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US98/00348

A. CLASSIFICATION OF SUBJECT MATTER

IPC(6) : G11B 7/24, 3/70, 3/74

US CL : 369/275.1, 94, 281

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 369/275.1, 94, 281, 286, 280, 272; 428/64.4, 64.1, 64.2, 64.8, 64.9; 430/321

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

A.P.S

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 4,450,553 A (HOLSTER ET AL) 22 May 1984, see figures 3 and 5; column 9, line 52 to column 10, line 63.	1, 3, 5-8, 10, 12, 15, 18-19, 26-27, 29, 32-33
X,P	US 5,627,814 A (LEE) 06 May 1997, see entire document.	1-34
X,P	US 5,608,715 A (YOKOGAWA ET AL) 04 March 1997, see figures 5,7,8,13.	1-34
X,P	US 5,689,497 A (WILTING ET AL) 18 November 1997, see entire document.	1-34

☐ Further documents are listed in the continuation of Box C.
 ☐ See patent family annex.

* Special categories of cited documents:	*T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
A document defining the general state of the art which is not considered to be of particular relevance	*X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
E earlier document published on or after the international filing date	*Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*A* document member of the same patent family
O document referring to an oral disclosure, use, exhibition or other means	
P document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

25 JUNE 1998

Date of mailing of the international search report

18 AUG 1998

 Name and mailing address of the ISA/US
 Commissioner of Patents and Trademarks
 Box PCT
 Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

TAN XUAN DINH

Telephone No. (703) 308-4859

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.